

## TECHNICAL DATA SHEET

# KEMAKOL RAPID 195

Fast-setting flexible adhesive



C2FT

S1

### PRODUCT DESCRIPTION

Flexible fast-setting plasticized cement-based adhesive for floor coverings, layer thickness 3 mm.

#### Field of use

For adhesion of ceramic tiles, gres porcelain, clinker, natural and artificial stone, used for indoor and outdoor, onto concrete surfaces, plasters, cement floor base, gypsum-cardboard panels and gas concrete. For quick installation and restoration works, for adhesion of floor and wall ceramic tiles, for outdoor and indoor use.

#### Product properties

Due to its high adherence, strength and flexibility it can be used on surfaces where common adhesives are not efficient.

- Fast-setting adhesive
- For walls and floors
- Reduced slip
- For outdoors and indoors
- High adhesion strenghts
- Easy to work with
- Effectiveness
- Frost-resistant
- Flexibility

### PRODUCT DATA

#### Basic information

Appearance	Grey powder
Packing	25 kg in bag (plastificated) / 1200 kg (48 x 25 kg) on pallet
Storage and expiration date	12 months from date of production if stored properly in undamaged original sealed packaging in dry and cool conditions. Date of production is printed on packaging.

#### Technical data

Type of product	Cementitious polymer modified adhesive	
Weight of fresh mortar	1,95 kg/l (at +20°C)	EN 12190:2000
Bulk density of powder	1,35 kg/l (at +20°C)	
Grain size	D <sub>max</sub> : 0,355 mm	EN 12192-1:2002
Layer thickness	approx. 3 mm	
Initial tensile adhesion strenght	>= 1 MPa	EN 1348:2007
Tensile adhesion strenght after water immersion	>= 1 MPa	EN 1348:2007
Tensile adhesion strenght after heat ageing	>= 1 MPa	EN 1348:2007
Tensile adhesion strenght after freeze-thaw cycles	>= 1 MPa	EN 1348:2007
Slip	<= 0,5 mm	EN 1308:2007
Open time after 20 min	>= 0,5 MPa	EN 1346:2007
Open time after 30 min	>= 0,5 MPa	EN 1346:2007
Deformability-deflection	>= 2,5 mm and < 5 mm	EN 12002:2009
pH (at +20°C)	11-13,5	

## INSTRUCTIONS FOR USE

Consumption	2-4 kg/m <sup>2</sup> depending on the substrate, floor covering size and application method
Base	The substrate has to be equally absorptive, dry, homogenous, solid, supporting, stabile, not frozen (over +5°C), clean and free of dust, oil, grease remains, wax, falling of colour, or dirt. Coatings have to be air dry and the reinforced cement floor base has to be at least 28 days old.
Base preparation	<p>Before applying the adhesive, anhydride cement floor base (mechanically ground), light concrete, gas concrete and gypsum coatings have to be impregnated with the polymer dispersion KEMACRYL (KEMAGRUND S) diluted with water in the ratio 1:1, for impregnation of compact surfaces is KEMAGRUND A, diluted with water in the ratio at least 1:1, recommended.</p> <p>Surface can be concrete (at least 3 months old), plaster, cement floor base, clinker, lightweight concrete or aerated concrete, cast asphalt or tiles. It is also suitable for terraces, facades and for underfloor and wall heating installations. If it is prepared in advance, surface can also be gypsum plaster, gypsum panels and calcium-sulphate floor base. It is not suitable for wood, metal and artificial materials.</p> <p>Surface has to be sufficiently flat to enable setting of ceramic in cca. 3 mm thick layer of adhesive. Bigger floor unevenness (0.5-3 cm) should be levelled by applying LINEA 820M (LINEA 20) mass to the connective KEMACRYL coating, diluted with water in the 1:1 ratio. When laying new ceramic tiles to the existing ones, the existing tiles have to be impeccably attached to the surface (must not sound hollow when knocked on). Before laying, they have to be washed with hot water and detergent to remove grease.</p> <p>Before setting of lining, floor bases with underfloor heating have to be heated and cooled in accordance with heating rules, cast asphalt surface has to be sandblasted.</p> <p>Surface can change its shape only in a limited amount after lining has been applied. On substrate constructions, which are contracting and extending, lining has to be laid as late as possible. A guideline is that lining can be applied app. 6 months after the construction on a concrete surface and wall with connected bricks. In substrate constructions, where expected effects are finalised, the aforementioned time limit can be shorter.</p>
Mix ratio	6,75-7,5 of water per 25 kg of dry mixture
Mix time	Mix dry mixture with clean water into a homogenous mass of medium plastic consistency without clods. Leave it to rest for app. 5 minutes to intumesce and remix it again just before the use. If necessary, add some water. Water must not be added to the adhesive that is already in the binding phase
Mix tool	Mix adhesive with electrical mixer with a suitable equipment for mixing in a clean container. Free fall mixers should not be used.
Installation	<p>Apply a thin adhesive layer on a cleaned surface using a trowel. Apply the next layer to a fresh contact layer using a notched finishing trowel.</p> <p>Ceramic tiles should be pressed into a fresh glue before a film forms on the adhesive.</p> <p>Adhesives in joints should be removed before it dries. By removing the adhesive from the joints the grouting compound can be applied and possible stains on the joints are prevented.</p> <p>If setting tiles on more demanding surfaces (outdoor, pools) and in other areas that require perfect adherence of ceramic tiles, the use of combined procedure is recommended. At the combined procedure the thin-layer adhesive is applied on both surfaces; on the surface to be lined as well as on the back side of the ceramics.</p>
Tool	Choose a notched finishing trowel with teeth depth of 4 to 6 mm, which assures 2 to 3 mm thick adhesive layer.
Cleaning of tool	Clean tools immediately after the use before adhesive hardens. Hardened material on tools can only be removed mechanically.
Usage time	45 minut
Open time	app. 20 minut
Coagulation	<p>Product appropriate for (+20°C):</p> <p>Grouting of floor surfaces after 4 hours</p> <p>Grouting of wall surfaces after 3,5 hours</p> <p>Grouting of tile on tile:</p> <ul style="list-style-type: none"> <li>-floor surfaces after 12 hours</li> <li>-wall surfaces after 11 hours</li> </ul> <p>Foot traffic on concrete surfaces after 4 hours</p> <p>Foot traffic on tile on tile after 12 hours</p> <p>Full load after 2-3 days</p>

## LIMITATIONS

Base temperature	+5°C min./ +30°C max.
Air temperature	+5°C min./ +30°C max.
Material temperature	+5°C min./ +30°C max.
Warnings	<ul style="list-style-type: none"> <li>• Times specified in the technical sheet were measured at the temperature of +23°C and relative air humidity of 50 %. Higher temperatures reduce, while lower temperatures prolong those times.</li> <li>• Use only recommended amount of water. Use only mixture from undamaged packaging. Do not overdo the layer thickness.</li> <li>• Gypsum board panels should be at least 10 mm thickness, with maximum moistness of 5%</li> <li>• To achieve later water-resistance under the tiles a layer of Hidrostop Elastik is recommended.</li> <li>• Protect freshly installed material from freezing, rain and other weather conditions. The material should not be used at (surface, air, material) temperatures lower than +5°C.</li> <li>• It is not necessary to wet the lining before application. When setting natural stone, there is a danger of stone being coloured, so prior test setting is recommended.</li> <li>• Due to different working conditions presence of a film on the adhesive should be checked with a finger if membrane is formed on the surface of the applied adhesive.</li> <li>• Application of adhesive in direkt sun and draught is not allowed</li> </ul>

**Recommendation: Remains of unhardened/unset material had to be removed in accordance with the legislation.**

Data source: All technical data in this technical sheet was obtained by laboratory research. Actual data may differ due to different working conditions.

Local restrictions: Due to specific local regulations the installed product can differ from country to country. For exact instructions for use a country specific technical sheet should be obtained.

#### PROOFS

##### Norms/Standards

In accordance with European standards EN 12004:2007

#### SAFETY DATA

Irritating. Contains cement. Irritating to eyes, skin and respiratory tract. In case of eye contact wash thoroughly with water at once and consult a doctor. In case of skin contact flood with a lot of water. Keep away from the reach of children. More data on storage, handling and use of mixture can be found in the safety sheet which contains safety, toxicological and ecological data. Warnings on the original packaging should also be considered.

#### LEGAL BASE

Information and recommendations related to use of KEMA products are presented in good faith and believed to be correct. The later is based on our knowledge and experience with the products. Information is supplied upon the condition that products are stored and used according to the recommendations and the persons receiving the same will make their own determination as to its suitability for their purposes prior to use. No representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which information refers. In no event will KEMA be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to the use any product, process, equipment or formulation in conflict with any patent, and KEMA makes no representation or warranty, expressed or implied that the use thereof will not infringe any patent. All orders fall under current sales and supply conditions. The user should always check the latest technical sheet available upon demand.